

FACTORY FURNITURE



Accoya (Acetylated Radiata Pine)

Certification FSC® C005669

Origins

New Zealand

Density

515 Kg/m³

Strength Class

C22 (Moderate)

Durability

Class 1 (Excellent - 25+ years)

Hardness

4100 N (Janka)

Colour

Creamy straw to light brown colour turning silvery-grey on weathering

Stability (Resistance to cracking, warping etc)

Excellent

Finish (Machinability and sanded finish)

Good

Use class

Class 4 - In ground or fresh water contact

Comments

Clear graded softwood treated with acetic anhydride (a vinegar) to produce an incredibly stable softwood with a lifespan of 50 years above ground

