

# FACTORY FURNITURE



## Western Red Cedar (Thuja plicata)

Certification FSC® C005669

### Origins

North America / Canada

### Density

390 Kg/m<sup>3</sup>

### Strength Class

C14 (Moderate)

### Durability

Class 3 (Good)

### Hardness

1560 N (Janka)

### Colour

Reddish-brown turning silvery-grey on weathering

### Stability (Resistance to cracking, warping etc)

Moderately stable to stable

### Finish (Machinability and sanded finish)

Good

### Use class

Class 3 - Not in ground contact, outside

### Comments

Clear graded (free of knots) and stable softwood, durable but suitable for light public use only due to softness. A popular timber for building cladding.

