

# FACTORY FURNITURE



## Sapele (Entandrophragma cylindricum)

Certification FSC® C005669

## Origins

West Africa

## Density

690 Kg/m<sup>3</sup>

## Strength Class

D40 (Good)

## Durability

Class 3 (Good - 10-15 years)

## Hardness

6710 N (Janka)

## Colour

Dark reddish brown to golden yellow turning grey on weathering

## Stability (Resistance to cracking, warping etc)

Moderately stable

## Finish (Machinability and sanded finish)

Good

## Use class

Class 2 - Inside or under cover

## Comments

A popular hardwood often used as an alternative to mahogany due to its durability, colour and material stability.

